



The Pioneer Of Geosynthetics
S I N C E 1 9 7 2

GSE Conductive White Textured Geomembrane (Single-Sided)

GSE Conductive White Textured is a co-extruded single-sided textured, patented, spark-testable high density polyethylene (HDPE) geomembrane that contains an integrated, specially formulated smooth conductive layer on the bottom surface of the geomembrane. GSE Conductive White Textured has a U.V. stabilized upper white surface that reflects light, improves damage detection, reduces wrinkles and subgrade desiccation. It can also be easily tested for post-installation damage using equipment capable of performing spark testing in the field per ASTM D7240. This product is used in applications that require post-installation testing on the liner system to increase the quality of the project.

Product Specifications

These product specifications meet or exceed GRI GM13.

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM AVERAGE VALUE			
			40 mil	60 mil	80 mil	100 mil
Thickness, (minimum average) mil (mm) Lowest individual reading (-10%)	ASTM D 5994	every roll	40 (1.00) 36 (0.91)	60 (1.50) 54 (1.40)	80 (2.00) 72 (1.80)	100 (2.50) 90 (2.30)
Density, g/cm ³	ASTM D 1505	200,000 lb	0.94	0.94	0.94	0.94
Tensile Properties (each direction)	ASTM D 6693, Type IV	20,000 lb				
Strength at Break, lb/in-width (N/mm)	Dumbell, 2 ipm		75 (13)	115 (20)	155 (27)	230 (40)
Strength at Yield, lb/in-width (N/mm)			90 (15)	132 (23)	177 (31)	225 (39)
Elongation at Break, %	G.L. 2.0 in (51 mm)		100	100	100	100
Elongation at Yield, %	G.L. 1.3 in (33 mm)		12	12	12	12
Tear Resistance, lb (N)	ASTM D 1004	45,000 lb	32 (142)	45 (200)	60 (266)	75 (333)
Puncture Resistance, lb (N)	ASTM D 4833	45,000 lb	95 (422)	130 (578)	160 (711)	190 (845)
Carbon Black Content ⁽¹⁾ , % (Range)	ASTM D 1603*/4218	20,000 lb	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	45,000 lb	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾
Asperity Height, mil (mm)	ASTM D 7466	second roll	18 (0.45)	18 (0.45)	18 (0.45)	18 (0.45)
Notched Constant Tensile Load ⁽³⁾ , hr	ASTM D 5397, Appendix	200,000 lb	1,000	1,000	1,000	1,000
Oxidative Induction Time, min	ASTM D 3895, 200° C; O ₂ , 1 atm	200,000 lb	>140	>140	>140	>140
TYPICAL ROLL DIMENSIONS						
Roll Length ⁽⁴⁾ , ft (m)			650 (198)	420 (128)	320 (98)	250 (76)
Roll Width ⁽⁴⁾ , ft (m)			22.5 (6.9)	22.5 (6.9)	22.5 (6.9)	22.5 (6.9)
Roll Area, ft ² , (m ²), ft			14,625 (1,359)	9,450 (878)	7,200 (669)	5,625 (523)

NOTES:

- ⁽¹⁾GSE Conductive White Textured may have an overall ash content greater than 3.0% due to the white and conductive outer layers. These values apply to the non-conductive black layers.
- ⁽²⁾Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽³⁾NCTL for GSE Conductive White Textured is conducted on representative smooth membrane samples.
- ⁽⁴⁾Roll lengths and widths have a tolerance of ± 1%.
- GSE Conductive White Textured Single-Sided is available in rolls weighing approximately 3,000 lb (1,360 kg).
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77° C when tested according to ASTM D 746.
- *Modified.