



GSE UltraFlex

Product Data Sheet

(available from 0.5 – 2.5 mm)

GSE UltraFlex is a black, high quality, linear low density polyethylene (LLDPE) geomembrane produced from specially formulated polyethylene resin with outstanding flexibility. The polyethylene resin is designed specifically for flexible geomembrane applications. Its high uniaxial and multiaxial elongation characteristics make it very suitable for applications where differential or localized subgrade settlements are expected such as landfill closure cappings, leach pads, or any application where elongation or puncture resistance is critical. GSE UltraFlex contains approximately 97.5% polyethylene, 2.5% carbon black, trace amounts of antioxidants and heat stabilizers, and is suitable for exposed applications. These product specifications meet or exceed GRI-GM 17.

Tested Property	Unit	Test Method	Values				
			0.5	0.75	1.0	1.5	2.0
Thickness (a)	mm	ASTM D 5199	0.5	0.75	1.0	1.5	2.0
Density	g/cm ³	ASTM D 792	≤ 0.939	≤ 0.939	≤ 0.939	≤ 0.939	≤ 0.939
Tensile Properties (each Direction) (Minimum Average)		ASTM D 638 / 6693; type IV; 200 mm/min; lo = 50 mm					
Strength at Break	N/mm		13	20	27	40	53
Elongation at Break	%		800	800	800	800	800
Tear Resistance (Minimum Average)	N	ASTM D 1004	50	70	100	150	200
Puncture Resistance (Minimum Average)	N	ASTM D 4833	120	190	250	370	500
Carbon Black Content	%	ASTM D 1603	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0
Carbon Black Dispersion	Category	ASTM D 5596	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)
Dimensional Stability (each Direction)	%	ASTM D 1204 (100 °C/1h)	± 2	± 2	± 2	± 2	± 2
Melt Flow Index (c)	g/10 min	ASTM D 1238 (190 °C / 5.0 kg) (190 °C / 2.16 kg)	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0
Oxidative Induction Time (OIT)	min	ASTM D 3895 (200°C; Pure O ₂ ; 1 atm)	≥ 100	≥ 100	≥ 100	≥ 100	≥ 100

Reference Property	Unit	Test Method	Values				
Multiaxial Elongation at Break	%	similar to ASTM D 5617; Ø = 500 mm	≥ 30	≥ 30	≥ 30	≥ 30	≥ 30
Low Temperature Brittleness	°C	ASTM D 746	- 77	- 77	- 77	- 77	- 77
UV Resistance (d)		GRI-GM 11					
HP-OIT retained after 1,600 hours (e)	%	ASTM D 5885	≥ 35	≥ 35	≥ 35	≥ 35	≥ 35
Roll Width (approx.) (f)	m	---	7.0	6.95			
Surface	---	---	double-sided smooth				

- (a): Tolerance ± 10% - Special thickness available upon request.
- (b): Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be category 1 or 2. No more than 1 view from category 3.
- (c): Standard test conditions: 190 °C / 5.0 kg.
- (d): Test conditions: 20 hours UV cycle at 75°C followed by 4 hours condensation at 60°C; total: 1,600 hours.
- (e): UV Resistance is based on percent retained value regardless of the original High Pressure - OIT value.
- (f): Roll widths and lengths have a tolerance of ± 1%.



GSE Ultraflex is produced at GSE Reclin plant, Germany.



This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures. This information is subject to change without prior notice. Please contact GSE for updated information.

1213-CPD-3880

Europe, CIS & Africa Headquarters
GSE Lining Technology GmbH
 Normannenweg 28
 20537 Hamburg
 Germany
 Tel.: +49 40 76742-0
 Fax: +49 40 76742-34
 e-mail: europe@gseworld.de

Corporate Headquarters
GSE Lining Technology, Inc.
 19103 Gundle Road
 Houston, Texas 77073
 USA
 Tel: +1 281 443-8564
 Fax: +1 281 875-6010

Other Production facilities & Sales Offices
 United Kingdom
 Russia
 Turkey
 Australia
 Thailand
 Egypt
 Chile



09-07-17-UF-05/20-ASTM-E

Visit us at www.gseworld.com
 A Gundle/SLT Environmental, Inc. Company