



GSE UltraFlex is a black, high quality, linear low density polyethylene (LLDPE) geomembrane produced from specially formulated polyethylene resin with outstanding flexibility. The polyethylene resin is designed specifically for flexible geomembrane applications. Its high uniaxial and multiaxial elongation characteristics make it very suitable for applications where differential or localized subgrade settlements are expected such as landfill closure cappings, leach pads, or any application where elongation or puncture resistance is critical. GSE UltraFlex contains approximately 97.5% polyethylene, 2.5% carbon black, trace amounts of antioxidants and heat stabilizers, and is suitable for exposed applications. These product specifications meet or exceed GRI-GM 17.

Tested Property	Unit	Test Method	Values				
			0.5	0.75	1.0	1.5	2.0
Thickness (a)	mm	DIN EN ISO 9863-1	0.5	0.75	1.0	1.5	2.0
Density	g/cm ³	DIN ISO 1183-1/A	≤ 0.939	≤ 0.939	≤ 0.939	≤ 0.939	≤ 0.939
Tensile Properties (each Direction) (Minimum Average)		DIN EN ISO 527-3 (Type 5; 100 mm/min; lo = 50 mm)					
Stress at Break	MPa		26	26	26	26	26
Elongation at Break	%		700	700	750	750	750
Tear Resistance (Minimum Average)	N	DIN ISO 34-1/B(a)	55	80	110	165	220
Puncture Resistance (Minimum Average)	N	DIN EN ISO 12236	900	1,450	2,000	3,100	4,100
Carbon Black Content	%	ASTM D 1603	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0
Carbon Black Dispersion	Category	ASTM D 5596	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)	1 / 2 (b)
Dimensional Stability (each Direction)	%	DIN 53377 (100 °C/1h)	± 2	± 2	± 2	± 2	± 2
Melt Flow Index (c)	g/10 min	DIN EN ISO 1133 (190 °C / 5.0 kg) (190 °C / 2.16 kg)	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0
Oxidative Induction Time (OIT)	min	ASTM D 3895 (200°C; Pure O ₂ ; 1 atm)	≥ 100	≥ 100	≥ 100	≥ 100	≥ 100
Reference Property	Unit	Test Method	Values				
Multiaxial Elongation at Break	%	similar to ASTM D 5617 ; Ø = 500 mm	≥ 30	≥ 30	≥ 30	≥ 30	≥ 30
Low Temperature Brittleness	°C	ASTM D 746	- 77	- 77	- 77	- 77	- 77
UV Resistance (d)		GRI-GM 11					
HP-OIT retained after 1,600 hours (e)	%	ASTM D 5885	≥ 35	≥ 35	≥ 35	≥ 35	≥ 35
Roll Width (approx.) (f)	m	---	7.0	6.95			
Surface	---	---	double-sided smooth				

- (a): Tolerance ± 10% - Special thickness available upon request.
- (b): Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be category 1 or 2. No more than 1 view from category 3.
- (c): Standard test conditions: 190 °C / 5.0 kg.
- (d): Test-Conditions: 20 hours UV cycle at 75°C followed by 4 hours condensation at 60°C; total: 1,600 hours.
- (e): UV Resistance is based on percent retained value regardless of the original High Pressure - OIT value.
- (f): Roll widths and lengths have a tolerance of ± 1%.



GSE UltraFlex is produced at GSE Reclin plant, Germany.



1213-CPD-3880

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures. This information is subject to change without prior notice. Please contact GSE for updated information.

Europe, CIS & Africa Headquarters
GSE Lining Technology GmbH
 Normannenweg 28
 20537 Hamburg
 Germany
 Tel.: +49 40 76742-0
 Fax: +49 40 76742-34
 e-mail: europe@gseworld.de

Corporate Headquarters
GSE Lining Technology, Inc.
 19103 Gundle Road
 Houston, Texas 77073
 USA
 Tel: +1 281 443-8564
 Fax: +1 281 875-6010

Other Production facilities & Sales Offices
 United Kingdom
 Russia
 Turkey
 Australia
 Thailand
 Egypt
 Chile



09-07-17-UFB-05/20-ISO-E