



The Pioneer of Geosynthetics
S I N C E 1 9 7 2

GSE UltraFlex White Textured Geomembrane (Double-Sided)

GSE UltraFlex White Textured is a co-extruded textured linear low density polyethylene (LLDPE) geomembrane available on one or both sides. It is manufactured from the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require increased frictional resistance, flexibility and elongation properties where differential or localized subgrade settlements may occur such as in a landfill closure application.

Product Specifications

These product specifications meet or exceed GRI GM 17.

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM AVERAGE VALUE		
Product Code			LDT100A01T	LDT150A01T	LDT200A01T
Thickness, mm (mil) ⁽¹⁾	ASTM D 5994	every roll	1.0 (40)	1.5 (60)	2.0 (80)
Lowest individual reading, mm (mil)			0.85 (34)	1.28 (51)	1.7 (68)
Density, g/cm ³	ASTM D 1505	every 5th roll	0.92	0.92	0.92
Tensile Properties (each direction) ⁽²⁾	ASTM D 6693, Type IV	every 5th roll			
Strength at Break, N/mm-width (lb/in)	Dumbell, 2 ipm		18 (103)	23 (131)	28 (160)
Elongation at Break, %	G.L. 51 mm (2.0 in)		400	400	400
Tear Resistance, N (lb)	ASTM D 1004	every 5th roll	100 (22)	150 (34)	200 (45)
Puncture Resistance, N (lb)	ASTM D 4833	every 5th roll	214 (48)	325 (73)	436 (98)
Carbon Black Content ⁽³⁾ , %	ASTM D 1603	every 5th roll	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0
Carbon Black Dispersion	ASTM D 5596	every 5th roll	Note ⁽⁴⁾	Note ⁽⁴⁾	Note ⁽⁴⁾
Asperity Height	ASTM D 7466	every second roll	Note ⁽⁵⁾	Note ⁽⁵⁾	Note ⁽⁵⁾
Oxidative Induction Time, minutes	ASTM D 3895, 200° C; O ₂ , 1 atm	90,000 kg	>100	> 100	>100
TYPICAL ROLL DIMENSIONS					
Roll Length (approximate), m (ft)			150 (492)	100 (328)	80 (262)
Roll Width, m (ft)			7.0 (23)	7.0 (23)	7.0 (23)
Roll Area, m ² (ft ²)			1,050 (11,316)	700 (7,544)	560 (6,026)
40' Standard Container, roll			16	16	16

NOTES:

- ⁽¹⁾Minimum average core thickness is -5% of the nominal thickness; lowest thickness for 8 out of 10 values is -10% of the nominal value; lowest thickness for any of the 10 values is -15% of the nominal value.
- ⁽²⁾The combination of stress concentrations due to co-extrusion texture geometry and the small specimen size results in large variation of test results. Therefore, these tensile properties are minimum average values.
- ⁽³⁾GSE UltraFlex White Textured may have an overall ash content greater than 3.0% due to the white layer.
- ⁽⁴⁾Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽⁵⁾0.25 mm average. 8 of 10 readings >0.18 mm. Lowest individual > 0.13 mm.
- GSE UltraFlex White Textured is provided in rolls weighing approximately 1,150 kg (2,535 lb) each.
- All GSE geomembranes have dimensional stability of ±2% when tested with ASTM D 1204 and LTB of <-77° C when tested with ASTM D 746.
- Alternate the measurement side for double sided textured sheet.

ADSUltraFlexWhiteDS R02/01/10

NORTH AMERICA 800.435.2008 281.443.8564 • EUROPE & AFRICA 49.40.767420 • ASIA PACIFIC 66.2.937.0091 • SOUTH AMERICA 56.2595.4200 • MIDDLE EAST 20.23.828.888

gseworld.com

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Specifications subject to change without notice.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, LLC in the United States and certain foreign countries.