



The Pioneer of Geosynthetics
S I N C E 1 9 7 2

GSE UltraFlex FrictionFlex Geomembrane (Double-Sided)

GSE UltraFlex FrictionFlex is a spray-on texture version of GSE UltraFlex. It is a linear low density polyethylene (LLDPE) geomembrane that is textured on both sides using GSE's patented texturing process and manufactured with the highest quality resin specifically formulated for flexible geomembranes. This process is the only one that produces a textured material without significant reduction of any physical properties. The product allows project for greater slopes to be designed since frictional characteristics are enhanced.

Product Specifications

These product specifications meet or exceed GRI GM 17.

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM AVERAGE VALUE			
Product Code			LDD100 A00T	LDD150 A00T	LDD200 A00T	LDD250 A00T
Thickness Minimum average, mm (mil)	ASTM D 5994	every roll	1.0 (40)	1.5 (60)	2.0 (80)	2.5 (100)
Lowest individual reading, mm (mil)			0.9 (36)	1.35 (54)	1.8 (72)	2.25 (90)
Density, g/cm ³	ASTM D 1505	every 5th roll	0.92	0.92	0.92	0.92
Tensile Properties (each direction) Strength at Break, N/mm-width (lb/in) Elongation at Break, %	ASTM D 6693, Type IV Dumbbell, 2 ipm G.L. 51 mm (2.0 in)	every 5th roll	25 (143) 700	40 (228) 700	53 (303) 700	66 (377) 700
Tear Resistance, N (lb)	ASTM D 1004	every 5th roll	100 (22)	150 (34)	200 (45)	250 (56)
Puncture Resistance, N (lb)	ASTM D 4833	every 5th roll	214 (48)	325 (73)	436 (98)	538 (121)
Carbon Black Content, %	ASTM D 1603	every 5th roll	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0	2.0 – 3.0
Carbon Black Dispersion	ASTM D 5596	every 5th roll	Note ⁽¹⁾	Note ⁽¹⁾	Note ⁽¹⁾	Note ⁽¹⁾
Asperity Height	ASTM D 7466	every second roll	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾
Oxidative Induction Time, minutes	ASTM D 3895, 200° C; O ₂ , 1 atm	90,000 kg	>100	>100	>100	>100
TYPICAL ROLL DIMENSIONS						
Roll Length (approximate), m (ft)			200 (656)	100 (328)	80 (262)	60 (197)
Roll Width, m (ft)			7.0 (23)	7.0 (23)	7.0 (23)	7.0 (23)
Roll Area, m ² (ft ²)			1,400 (15,088)	700 (7,544)	560 (6,026)	420 (4,531)
40' Standard Container, roll			9	16	16	16

NOTES:

- ⁽¹⁾ Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽²⁾ 0.25 mm average. 8 of 10 readings \geq 0.18 mm. Lowest individual \geq 0.13 mm.
- GSE UltraFlex FrictionFlex is provided in rolls weighing approximately 1,150 kg (2,535 lb) each.
- All GSE geomembranes have dimensional stability of \pm 2% when tested with ASTM D 1204 and LTB of $<$ -77° C when tested with ASTM D 746.
- Alternate the measurement side for double-sided textured sheet.

ADSUltraFlexFFDS R09/11/10

NORTH AMERICA 800.435.2008 281.443.8564 • EUROPE & AFRICA 49.40.767420 • ASIA PACIFIC 66.2.937.0091 • SOUTH AMERICA 56.2595.4200 • MIDDLE EAST 20.23.828.888