

GSE CoalDrain PermaNet 7.6 mm Geocomposite (Double-Sided)

METRIC

GSE CoalDrain geocomposite consists of a 7.6 mm thick GSE PermaNet geonet heat-laminated with a non-woven geotextile on the bottom side and an innovative composite fabric on the top side. The top geotextile serves as filter against fine materials like coal ash and FGD gypsum while the core serves the drainage function. The PermaNet geonet has two sets of diagonally crossing panel strands in a round, cross-sectional shape for superior compressive resistance. The innovative geocomposite has been tested extensively in the laboratory and the field and has been proven to meet the performance requirements of an effective filter against coal combustion residuals. This product is ideal for very high compressive strength applications.



AT THE CORE:
A high flow geocomposite that effectively filters coal combustion residuals.

Product Specifications

| Tested Property | Test Method | Frequency | Minimum Average Roll Value ⁽¹⁾ |
|--|--|-------------------------|---|
| Geocomposite | | | |
| Transmissivity ⁽²⁾ , m ² /sec | ASTM D 4716 | 1/50,000 m ² | 9 X 10 ⁻⁴ |
| Ply Adhesion, g/cm | ASTM D 7005 | 1/4,600 m ² | 89 |
| Geonet Core^(1,3) - GSE PermaNet 7.6 mm | | | |
| Geonet Core Thickness, mm | ASTM D 5199 | 1/4,600 m ² | 7.6 |
| Density, g/cm ³ | ASTM D 1505 | 1/4,600 m ² | 0.94 |
| Tensile Strength (MD), N/mm | ASTM D 7179 | 1/4,600 m ² | 17.5 |
| Carbon Black Content, % | ASTM D 4218 | 1/4,600 m ² | 2.0 |
| Compressive Strength kPa | ASTM D 6364 | | 2400 |
| Top Composite Geotextile^(1,3) | | | |
| Structure | Hybrid monolithic woven-nonwoven needlepunched | | |
| Mass per Unit Area, g/m ² | ASTM D 5261 | 1/8365 m ² | 480 |
| Grab Tensile Strength, N | ASTM D 4632 | 1/8365 m ² | 890 |
| CBR Puncture Strength, N | ASTM D 6241 | 1/8365 m ² | 3,447 |
| Trapezoidal Tear Strength, N | ASTM D 4533 | 1/8365 m ² | 378 |
| AOS, US Sieve (mm) | ASTM D 4751 | 1/50,000 m ² | 170 (0.09) |
| Permittivity, (sec ⁻¹) | ASTM D 4491 | 1/50,000 m ² | 0.3 |
| Water Flow Rate, lpm/m ² | ASTM D 4491 | 1/50,000 m ² | 814 |
| UV Resistance, % retained | ASTM D 4355 (after 500 hours) | per formulation | 70 |
| Field Basin Tests | | per formulation | see note ⁽⁵⁾ |

[Product specifications continued on back]



AT THE CORE:
A high flow
geocomposite that
effectively filters coal
combustion residuals.

Product Specifications [continued]

| Tested Property | Test Method | Frequency | Minimum Average Roll Value ⁽¹⁾ |
|--|----------------------------------|-------------------------|---|
| Bottom Geotextile | | | |
| Mass per Unit Area, g/m ² | ASTM D 5261 | 1/8,300 m ² | 200 |
| Grab Tensile Strength, N | ASTM D 4632 | 1/8,300 m ² | 710 |
| Grab Elongation | ASTM D 4632 | 1/8,300 m ² | 50% |
| CBR Puncture Strength, N | ASTM D 6241 | 1/50,000 m ² | 1,936 |
| Trapezoidal Tear Strength, N | ASTM D 4533 | 1/8,300 m ² | 290 |
| AOS, US Sieve (mm) | ASTM D 4751 | 1/50,000 m ² | 70 (0.212) |
| Permittivity, (sec ⁻¹) | ASTM D 4491 | 1/50,000 m ² | 1.5 |
| Water Flow Rate, lpm/m ² | ASTM D 4491 | 1/50,000 m ² | 4,480 |
| UV Resistance, % retained | ASTM D 4355 (after 500 hours) | per formulation | 70 |
| TYPICAL ROLL DIMENSIONS⁽⁴⁾ | | | |
| Roll Width, m | | | 4.57 |
| Roll Length, m | | | 39.6 |
| Roll Area, m ² | | | 181 |

NOTES:

- ⁽¹⁾All geotextile are minimum average roll values except AOS which is maximum average roll value and UV resistance is typical value. Geonet core thickness is nominal value.
- ⁽²⁾Gradient of 0.1, normal load of 1440 kPa water at 20°C between steel plates for 15 minutes. Contact GSE for performance transmissivity value for use in design.
- ⁽³⁾Component properties prior to lamination.
- ⁽⁴⁾Roll widths and lengths have a tolerance of ±1%.
- ⁽⁵⁾Filter compatibility with a minimum of three types of CCP materials (fly ash, stabilized FGD, and FGD gypsum) under simulated field conditions.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP] For more information on this product and others, please visit us at GSEworld.com, call 800.435.2008 or contact your local sales office.