

High Performance GSE UltraFlex Leak Location Textured Geomembrane

METRIC

High Performance GSE UltraFlex Textured is a co-extruded linear low density polyethylene (LLDPE) geomembrane specifically designed to be used in the most stringent applications. It contains an integrated, specially formulated conductive layer on the bottom surface of the geomembrane. High Performance GSE UltraFlex Leak Location Textured can be easily tested for post-installation damage utilizing spark testing technology per ASTM D 7240 and utilizing electrical resistivity testing per ASTM D 7002 on exposed geomembranes and ASTM D 7007 after water or cover soil placement. Included in this product is a custom additive package that has been engineered to enable extended geomembrane lifetime and improved resilience in elevated temperatures and in harsh chemical environments. This product is used in applications that require increased frictional resistance, flexibility and elongation properties where differential or localized subgrade settlements may occur.



AT THE CORE:
An LLDPE geomembrane that is used in applications requiring increased frictional resistance, flexibility and elongation properties, such as landfill closures and mining applications.

Product Specifications

These product specifications exceed GRI GM17

Tested Property	Test Method	Frequency	Minimum Average Value			
			1.00 mm	1.50 mm	2.00 mm	2.50 mm
Thickness, mm Lowest individual reading	ASTM D 5994	every roll	1.00 0.90	1.50 1.35	2.00 1.80	2.50 2.50
Density, g/cm ³ (max)	ASTM D 1505	90,000 kg	0.939	0.939	0.939	0.939
Tensile Properties (each direction) Strength at Break, N/mm Elongation at Break, %	ASTM D 6693, Type IV Dumbbell, 50 mm/min G.L. 50 mm	9,000 kg	20 500	29 500	39 500	47 500
Tear Resistance, N	ASTM D 1004	20,000 kg	111	169	222	266
Puncture Resistance, N	ASTM D 4833	20,000 kg	289	422	556	622
Multi-axial Break Resistance, %	ASTM D 5617	per formulation	90	90	90	90
Carbon Black Content, % (Range)	ASTM D 1603*/4218	9,000 kg	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	20,000 kg	Note ⁽¹⁾	Note ⁽¹⁾	Note ⁽¹⁾	Note ⁽¹⁾
Asperity Height ⁽²⁾ , mm	ASTM D 7466	second roll	0.45	0.45	0.45	0.45
Oxidative Induction Time, mins	ASTM D 3895, 200°C; O ₂ , 1 atm	90,000 kg	>140	>140	>140	>140
High Pressure Oxidative Induction Time, mins	ASTM D 5885, 150°C; O ₂ , 3.4 MPa	per formulation	>550	>550	>550	>550
Oven aging at 85°C High Pressure OIT (min. avg.) - % retained after 90 days	ASTM D 5721 ASTM D 5885	per formulation	80	80	80	80
UV Resistance High Pressure OIT (min. avg.) - % retained after 1,600 hours	GM 11 ASTM D 5885	per formulation	60	60	60	60
TYPICAL ROLL DIMENSIONS						
Roll Length ⁽³⁾ , m	Double-Sided Textured Single-Sided Textured		213 243	158 165	122 125	101 101
Roll Width ⁽³⁾ , m			6.86	6.86	6.86	6.86
Roll Area, m ²	Double-Sided Textured Single-Sided Textured		1,461 1,667	1,084 1,132	837 858	693 693

[Product specifications continued on back]

Product Specifications [continued]

NOTES:

- ⁽¹⁾Dispersion applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽²⁾Consult GSE for information regarding asperity heights exceeding the specified values.
- ⁽³⁾Roll lengths and widths have a tolerance of ±1%.
- High Performance GSE UltraFlex Textured is available in rolls weighing approximately 1,800 kg.
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77° C when tested according to ASTM D 746.
- *Modified.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP] For more information on this product and others, please visit us at GSEworld.com, call 800.435.2008 or contact your local sales office.