

GSE Green Textured Geomembrane (Single-Sided)

GSE Green Textured is a co-extruded textured high density polyethylene (HDPE) geomembrane on one or both sides. It is manufactured from the highest quality resin specifically formulated for flexible geomembranes. It has a U.V. stabilized green upper surface that improves the aesthetics for the community. GSE Green Textured provides an increased frictional resistance surface and is primarily used in exposed applications which can eliminate the need for cover soil and vegetative layers.



AT THE CORE:
An HDPE geomembrane used primarily in exposed applications, eliminating the need for cover soil and vegetative layers.

Product Specifications

These product specifications meet or exceed GRI GM13.

Tested Property	Test Method	Frequency	Minimum Average Value	
Thickness, mm (mil) ⁽¹⁾ Lowest individual reading, mm (mil)	ASTM D 5994	every roll	1.0 (40) 0.85 (34)	1.5 (60) 1.28 (51)
Density, g/cm ³	ASTM D 1505	every 5th roll	0.94	0.94
Tensile Properties (each direction) ⁽²⁾ Strength at Break, N/mm-width (lb/in) Strength at Yield, N/mm-width (lb/in) Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbbell, 2 ipm G.L. 51 mm (2.0 in) G.L. 33 mm (1.3 in)	every 5th roll	11 (63) 15 (86) 150 13	16 (91) 23 (131) 150 13
Tear Resistance, N (lb)	ASTM D 1004	every 5th roll	125 (28)	187 (42)
Puncture Resistance, N (lb)	ASTM D 4833	every 5th roll	320 (72)	480 (108)
Carbon Black Content, ⁽³⁾ %	ASTM D 1603 / D 4218	every 5th roll	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	every 5th roll	Note ⁽⁴⁾	Note ⁽⁴⁾
Asperity Height	ASTM D 7466	every 2nd roll	Note ⁽⁵⁾	Note ⁽⁵⁾
Notched Constant Tensile Load, ⁽⁶⁾ hrs	ASTM D 5397 Appendix	90,000 kg	500	500
Oxidative Induction Time, minutes	ASTM D 3895, 200° C; O ₂ , 1 atm	90,000 kg	>100	> 100
TYPICAL ROLL DIMENSIONS				
Roll Length ⁽⁷⁾ , m (ft)			200 (656)	100 (328)
Roll Width ⁽⁷⁾ , m (ft)			7.0 (23)	7.0 (23)
Roll Area, m ² (ft ²)			1,400 (15,088)	700 (7,544)
40' Standard Container, roll			9	14

NOTES:

- ⁽¹⁾Minimum average core thickness is -5% of the nominal thickness; lowest thickness for 8 out of 10 values is - 10% of the nominal value; lowest thickness for any of the 10 values is -15% of the nominal value.
- ⁽²⁾The combination of stress concentrations due to co-extrusion texture geometry and the small specimen size results in large variation of test results. Therefore, these tensile properties are minimum average values.
- ⁽³⁾GSE Green may have an overall ash content greater than 3.0% due to the green layer.
- ⁽⁴⁾Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽⁵⁾0.40 mm average. 8 of 10 readings >0.35 mm. Lowest individual >0.30 mm.
- ⁽⁶⁾NCTL for HD Textured is conducted on representative smooth membrane samples.
- ⁽⁷⁾Roll lengths and widths have a tolerance of +/- 1%.
- GSE HD Standard Textured is provided in rolls weighing approximately 1,100 - 1,530 kg.
- All GSE geomembranes have dimensional stability of 32% when tested with ASTM D 1204 and LTB of <-77° C when tested with ASTM D 746.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP] For more information on this product and others, please visit us at GSEworld.com, call 66.2.937.0091 or contact your local sales office.