

GSE High Temperature Geomembrane

GSE High Temperature Geomembrane is a specially engineered HDPE geomembrane that is able to retain its mechanical and physical properties when exposed to temperatures up to 100°C. It is an innovative formulation that takes advantage of the high temperature performance of revolutionary resins and the thermal stability of GSE's proprietary stabilization package. It provides enhanced mechanical performance and improved chemical stability at elevated temperatures in addition to the traditional properties of polyethylene geomembranes.



AT THE CORE:
An HDPE geomembrane used in applications that operate at peak temperatures up to 100°C.

Product Specifications

Tested Property	Test Method	Frequency	Value ^(1,2)			
			1.5 mm	2.0 mm	2.5 mm	3.0 mm
Thickness, mm (minimum average thickness ± 5%)	DIN EN ISO 9863-1	every roll	1.5	2.0	2.5	3.0
Density, g/cm ³	DIN EN ISO 1183-1/A	90,000 kg	≥ 0.940	≥ 0.940	≥ 0.940	≥ 0.940
Tensile Properties (each direction) Strength at Break, MPa Strength at Yield, MPa Elongation at Break, % Elongation at Yield, %	DIN EN ISO 527-3, Type V 100 mm/min; lo = 50 mm	9,000 kg	35 (26) 17 (16) 600 (500) 11 (10)	35 (26) 17 (16) 600 (500) 11 (10)	35 (26) 17 (16) 600 (500) 11 (10)	35 (26) 17 (16) 600 (500) 11 (10)
Tear Resistance, N	DIN ISO 34-1/B (a)	20,000 kg	225 (210)	300 (280)	375 (350)	450 (420)
Puncture Resistance, N	DIN EN ISO 12236	20,000 kg	4,150 (3,700)	5,450 (4,900)	6,750 (6,050)	8,000 (7,200)
Carbon Black Content, % (Range)	ASTM D 4218	9,000 kg	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	20,000 kg	Note ⁽³⁾	Note ⁽³⁾	Note ⁽³⁾	Note ⁽³⁾
Oxidative Induction Time, min	ASTM D 3895, 200°C; O ₂ , 1 atm	90,000 kg	≥ 160	≥ 160	≥ 160	≥ 160
High Pressure Oxidative Induction Time (HPOIT), min	ASTM D 5885, 150°C; O ₂ , 3.4 MPa	per formulation	≥ 800	≥ 800	≥ 800	≥ 800
Reference Property						
Tensile Properties @ 100 °C (each direction) Strength at Yield, MPa Elastic Modulus, MPa	ISO 527, 1/2	per formulation	≥ 5 ≥ 38	≥ 5 ≥ 38	≥ 5 ≥ 38	≥ 5 ≥ 38
Stress Crack Resistance ⁽⁴⁾ @ 80 °C (SP-NCTL), h	ASTM D 5397 (modified)	per formulation	≥ 500	≥ 500	≥ 500	≥ 500
Oven Aging HPOIT retained after 6 months, %	ASTM D 5721/5885	per formulation	≥ 90	≥ 90	≥ 90	≥ 90
100°C Oven Aging HPOIT ⁽⁵⁾ retained after 90 days, %	ASTM D 5721 (modified)/5885	per formulation	≥ 90	≥ 90	≥ 90	≥ 90
UV Resistance HPOIT retained after 1,600 hours, %	ASTM D 7238/5885	per formulation	≥ 80	≥ 80	≥ 80	≥ 80
Typical Roll Dimensions						
Roll Length ⁽⁶⁾ , m			140	105	80	70
Roll Width ⁽⁶⁾ , m			7.5	7.5	7.5	7.5
Roll Area, m ²			975	750	600	525

NOTES:

- ⁽¹⁾ All GSE geomembranes have dimensional stability of ±2% when tested according to DIN 53377 and LTB of <-77°C when tested according to ASTM D 746.
- ⁽²⁾ All values unless otherwise noted are nominal values. Values in brackets are minimum average values within 95% confidence interval.
- ⁽³⁾ Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽⁴⁾ NCTL is tested according to ASTM D 5397, but modified to 80°C and 3.4 Mpa (500psi) stress
- ⁽⁵⁾ GSE High Temperature Geomembrane is tested for HPOIT retention after incubation in elevated oven temperatures (100°C) for 90 days.
- ⁽⁶⁾ Roll lengths and widths have a tolerance of ±1%.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP]

For more information on this product and others, please visit us at GSEworld.com, call 800.435.2008 or contact your local sales office.