

GSE Leak Location White Smooth Geomembrane

METRIC

GSE Leak Location White is a smooth spark-testable high density polyethylene (HDPE) geomembrane that contains an integrated, specially formulated conductive layer on the bottom surface of the geomembrane. GSE Leak Location White has a UV stabilized upper white surface that reflects light, improves damage detection, and reduces wrinkles and subgrade desiccation. It can be easily tested for post-installation damage using equipment capable of performing spark testing in the field per ASTM D 7240. This product is used in applications that require post-installation testing on the liner system to increase the quality of the project.



AT THE CORE:

An HDPE geomembrane that combines the excellent quality assurance features of our best geomembranes.

Product Specifications

These product specifications meet GRI GM13.

| Tested Property | Unit | Test Method | Values (*) | | |
|--|-------------------|---|---------------------|--------------------|--------------------|
| Thickness (min. ave.) ^(a) | mm | ASTM D 5199 | 1.0 | 1.5 | 2.0 |
| Density (min.) | g/cm ³ | ASTM D 792 | ≥ 0.94 | ≥ 0.94 | ≥ 0.94 |
| Tensile Properties (each Direction) | | ASTM D 638 / D 6693; Type IV | | | |
| Strength at Yield | N/mm | 50 mm/min | 16 (15) | 24 (22) | 32 (30) |
| Elongation at Yield | % | lo = 33 mm | 15 (12) | 15 (12) | 15 (12) |
| Strength at Break | N/mm | 50 mm/min | 33 (27) | 49 (40) | 66 (53) |
| Elongation at Break | % | lo = 50 mm | 800 (700) | 800 (700) | 800 (700) |
| Tear Resistance | N | ASTM D 1004 | 140 (130) | 205 (190) | 275 (250) |
| Puncture Resistance | N | ASTM D 4833 | 420 (320) | 560 (480) | 690 (640) |
| Carbon Black Content ^(b) | % | ASTM D 4218 | 2.0 - 3.0 | 2.0 - 3.0 | 2.0 - 3.0 |
| Carbon Black Dispersion | Category | ASTM D 5596 | 1/2 ^(c) | 1/2 ^(c) | 1/2 ^(c) |
| Dimensional Stability (each Direction) | % | ASTM D 1204 (120°C/1 h) | ± 2 | ± 2 | ± 2 |
| Melt Flow Index ^(d) | g/10 min | ASTM D 1238 (190°C / 5.0 kg) (190°C / 2.16 kg) | ≤ 3.0 ≤ 1.0 | ≤ 3.0 ≤ 1.0 | ≤ 3.0 ≤ 1.0 |
| Stress Crack Resistance (NCTL) | h | ASTM D 5397; Appendix | ≥ 500 | ≥ 500 | ≥ 500 |
| Oxidative Induction Time (OIT) | min | ASTM D 3895 (200°C; Pure O ₂ ; 1 atm) | ≥ 100 | ≥ 100 | ≥ 100 |
| Reference Property | | | | | |
| Low Temperature Brittleness | °C | ASTM D 746 | - 77 | - 77 | - 77 |
| UV Resistance ^(e) HP-OIT retained after 1,600 hours ^(f) | % | ASTM D 7238 ASTM D 5885 | ≥ 50 | ≥ 50 | ≥ 50 |
| Roll Width (approx.) ^(g) | m | --- | 6.95 | | |
| Surface | --- | --- | double-sided smooth | | |

NOTES:

- (*): All values - unless otherwise noted - are nominal values. Values in brackets are minimum values within the 95% confidence interval.
- (a): Tolerance ± 10%.
- (b): GSE Leak Location White Smooth may have an overall ash content of 3.0% due to the conductive layer. These values apply to the black non-conductive layer only.
- (c): Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be category 1 or 2. No more than 1 view from category 3.
- (d): Standard test conditions: 190°C / 5.0 kg.
- (e): Test-Conditions: 20 hours UV cycle at 75°C followed by 4 hours condensation at 60°C.
- (f): UV Resistance is based on percent retained value regardless of the original High Pressure - OIT value.
- (g): Roll widths and lengths have a tolerance of ± 1%.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.

[DURABILITY RUNS DEEP] For more information on this product and other, please visit us at GSEworld.com, call 49.40.767420 or contact your local sales office.

