

# GSE White Textured Geomembrane

METRIC

GSE White Textured is a co-extruded textured high density polyethylene (HDPE) geomembrane available on one or both sides. It is manufactured with the highest quality resin specifically formulated for flexible geomembranes. GSE White Textured has a UV stabilized upper white surface that reflects light, improves damage detection, reduces wrinkles and subgrade desiccation. This product provides increased frictional resistance, excellent chemical resistance, and endurance properties. It is used in applications that require enhanced quality assurance measures over standard geomembranes.



**AT THE CORE:**  
An HDPE geomembrane that provides increased frictional resistance and is ideal for exposed applications when aesthetics is an issue.

## Product Specifications

These product specifications meet GRI GM13

Tested Property	Test Method	Frequency	Minimum Average Value				
			0.75 mm	1.00 mm	1.50 mm	2.00 mm	2.50 mm
Thickness, (minimum average), mm Lowest individual reading	ASTM D 5994	every roll	0.750 0.675	1.00 0.90	1.50 1.35	2.00 1.80	2.50 2.25
Density, g/cm <sup>3</sup> . (min.)	ASTM D 1505	90,000 kg	0.940	0.940	0.940	0.940	0.940
Tensile Properties (each direction) Strength at Break, N/mm Strength at Yield, N/mm Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbbell, 50 mm/min G.L. 51 mm G.L. 33 mm	9,000 kg	8 11 100 12	10 15 100 12	16 22 100 12	21 29 100 12	26 37 100 12
Tear Resistance, N	ASTM D 1004	20,000 kg	93	125	187	249	311
Puncture Resistance, N	ASTM D 4833	20,000 kg	200	267	400	534	667
Carbon Black Content <sup>(1)</sup> , % (Range)	ASTM D 1603*/4218	9,000 kg	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	20,000 kg	Note <sup>(2)</sup>	Note <sup>(2)</sup>	Note <sup>(2)</sup>	Note <sup>(2)</sup>	Note <sup>(2)</sup>
Asperity Height, mm	ASTM D 7466	second roll	0.40	0.45	0.45	0.45	0.45
Notch Constant Tensile Load <sup>(3)</sup> , hr	ASTM D 5397, Appendix	90,000 kg	500	500	500	500	500
Oxidative Induction Time, min	ASTM D 3895, 200°C; O <sub>2</sub> , 1 atm	90,000 kg	>100	>100	>100	>100	>100
<b>TYPICAL ROLL DIMENSIONS</b>							
Roll Length <sup>(4)</sup> , m	Double-Sided Textured Single-Sided Textured		253 308	213 238	158 165	122 125	101 101
Roll Width <sup>(4)</sup> , m			6.86	6.86	6.86	6.86	6.86
Roll Area, m <sup>2</sup>	Double-Sided Textured Single-Sided Textured		1,736 2,113	1,461 1,633	1,084 1,132	837 858	693 693

NOTES:

- <sup>(1)</sup>GSE White may have an overall ash content greater than 3.0% due to the white layer. These values apply to the black layer only.
- <sup>(2)</sup>Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- <sup>(3)</sup>NCTL for GSE White Textured is conducted on representative smooth geomembrane samples.
- <sup>(4)</sup>Roll lengths and widths have a tolerance of ±1%.
- GSE White Textured is available in rolls weighing approximately 1,800 kg.
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77° C when tested according to ASTM D 746.
- \*Modified.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



**[ DURABILITY RUNS DEEP ]** For more information on this product and others, please visit us at [GSEworld.com](http://GSEworld.com), call 800.435.2008 or contact your local sales office.