## **GSE RoaDrain 5-MD Geocomposite**

GSE RoaDrain 5 geocomposite consists of a tri-planar geonet heat-laminated on both sides with a 6 oz. nonwoven needle-punched geotextile. This product quickly removes subsurface water from pavement base and sub-base layers, while providing a void-maintaining system to work as a capillary break. RoaDrain 5 also works as a separation layer.

## \*]

## AT THE CORE:

A tri-planar geonet heat-laminated on both sides with a nonwoven needlepunched geotextile.

## **Product Specifications**

Tested Property	Test Method	Value	Qualifier (1)
Tri-Planar Core <sup>(2)</sup>			
Density, g/cm³	ASTM D 792	0.94 - 0.96	Range
Carbon Black, %	ASTM D 4218	2-3	Range
Rib Spacing (top & bottom), in (mm)	Calipered	0.4 (10)	Typical
Central Rib Spacing, in (mm)	Calipered	0.5 (12.5)	Typical
Unsupported Aperture Area, in <sup>2</sup> (mm <sup>2</sup> )	Calipered	0.3 (195)	Max
Thickness, mil (mm)	ASTM D 5199	280 (7.1)	±10%
Geotextile <sup>(2)</sup>			
Strength	AASHTO M 288	Exceeds Class 2	
UV Resistance (500 hrs), %	ASTM D 4355	70	MARV
AOS, US Sieve (mm)	ASTM D 4751	70 (0.212)	MaxARV
Permittivity, sec <sup>-1</sup>	ASTM D 4491	1.4	MARV
Water Flow Rate, gpm/ft² (I/min/m²)	ASTM D 4491	110 (4481)	MARV
SSDL Performance			
Capillary Barrier	ASTM 5918	Effective	Notes (3)
Coefficient of Permeability <sup>(5)</sup> , ft/day	ASTM D 4716	56,700	Notes (4)
Flow Orientation			
Direction of Primary Flow		Along the length or Machine Direction (MD) of the roll	
NOMINAL ROLL DIMENSIONS			
Roll Width, ft (m)		12.75 (3.89)	
Roll Length, ft (m)		152 (46.3)	
Roll Area, ft² (m²)		1,938 (180)	

NOTES:

- <sup>(I)</sup> Qualifiers: MARV=Minimum Average Roll Value, MAV=Minimum Average Value, MAX=Maximum Value,
- MaxARV = Maximum Average Roll Value
- <sup>(2)</sup>Geotextile and core properties listed are prior to lamination.
- <sup>(3)</sup> As tested by the USACE Cold Regions Research and Engineering Laboratory (CRREL).
- <sup>(4)</sup>Coefficient of permeability is calculated with the measured SSDL transmissivity and the nominal core thickness. SSDL transmissivity is tested along the primary flow direction with the boundary conditions as follows: steel plate/Ottawa sand/SSDL/Ottawa sand/SSDL/Ottawa sand/steel plate, one hour seating period @ 5,000 psf and gradient 2%.
- <sup>(5)</sup> Direction of primary flow along the length or Machine Direction (MD) of the roll.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.

DURABILITY RUNS DEEP For more information on this product and others, please visit us at GSEworld.com, call 800.435.2008 or contact your local sales office.



This Information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this Information. Specifications subject to change without notice. GSE and other trademarks in this document are registered trademarks of GSE Environmental, LLC in the United States and certain foreign countries. REV 10JAN2017