

GSE HD Color Geomembrane (Green)

GSE HD Color(*) is a smooth high density polyethylene (HDPE) geomembrane manufactured with the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require excellent chemical resistance and endurance properties. It has a UV stabilized green upper surface(**) that improves the aesthetics for the community.



AT THE CORE:
An HDPE geomembrane which is ideal for exposed applications when aesthetics is an issue.

Product Specifications

Tested Property	Unit	Test Method	Values (**)			
Thickness (a)	mm	ASTM D 5199	0.75	1.0	1.5	2.0
Density	g/cm ³	ASTM D 792	≥ 0.94	≥ 0.94	≥ 0.94	≥ 0.94
Tensile Properties (each Direction)		ASTM D 638 / D 6693; type IV				
Stress at Yield	N/mm	50 mm/min	13 (11)	16 (15)	24 (22)	32 (30)
Elongation at Yield	%	lo = 33 mm	14 (12)	16 (13)	16 (13)	16 (13)
Stress at Break	N/mm	50 mm/min	26 (20)	33 (27)	49 (40)	66 (53)
Elongation at Break	%	lo = 50 mm	800 (700)	800 (700)	800 (700)	800 (700)
Tear Resistance	N	ASTM D 1004	100 (95)	145 (130)	205 (190)	275 (250)
Puncture Resistance	N	ASTM D 4833	340 (240)	420 (320)	560 (480)	690 (640)
Dimensional Stability (each Direction)	%	ASTM D 1204 (120°C/1 h)	± 2	± 2	± 2	± 2
Melt Flow Index (b)	g/10 min	ASTM D 1238 (190°C / 5.0 kg) (190°C / 2.16 kg)	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0	≤ 3.0 ≤ 1.0
Stress Crack Resistance (NCTL)	h	ASTM D 5397; Appendix	≥ 500	≥ 500	≥ 500	≥ 500
Oxidative Induction Time (OIT)	min	ASTM D 3895 (200°C; Pure O ₂ ; 1 atm)	≥ 100	≥ 100	≥ 100	≥ 100
Reference Property						
Low Temperature Brittleness	°C	ASTM D 746	- 77	- 77	- 77	- 77
Carbon Black Content(c) (black layer)	%	ASTM D 1603	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion (black layer)	Category	ASTM D 5596	1/2 (d)	1/2 (d)	1/2 (d)	1/2 (d)
UV-Resistance (e)	%	ASTM D 7238				
HP-OIT retained after 1,600 hours (f)		ASTM D 5885	≥ 50	≥ 50	≥ 50	≥ 50
Roll Width (approx.) (g)	m	---	6.95			
Surface	---	---	double-sided smooth			

NOTES:

- (*): RAL 6005 Moss-Green. The UV-resistance as well as the color stability is variable in time dependent on the selected color.
- (**): Due to the production process the brightness of the colored layer may vary.
- (***) : All values - unless otherwise noted - are nominal values. Values in brackets are minimum values within the 95% confidence interval.
- (a): Tolerance ± 10% for the lowest individual reading.
- (b): Standard test conditions: 190°C / 5.0 kg.
- (c): GSE HD Color may have an overall ash content greater than 3% due to the coloured layer.
- (d): Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be category 1 or 2. No more than 1 view from category 3.
- (e): Test conditions: 20 hours UV-cycle at 75°C followed by 4 hours condensation at 60°C.
- (f): UV Resistance is based on percent retained value regardless of the original High Pressure - OIT value.
- (g): Roll widths and lengths have a tolerance of ± 1%.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP] For more information on this product and other, please visit us at GSEworld.com, call 49.40.767420 or contact your local sales office.

