

# GSE Leak Location White Textured Geomembrane

## METRIC

GS Leak Location White Textured is a co-extruded textured high density polyethylene (HDPE) geomembrane. A textured surface is available on one or both sides for applications that require increased frictional resistance. It contains an integrated, specially formulated conductive layer on the bottom surface of the geomembrane to enable spark testing. GSE Leak Location White Textured has a UV stabilized upper white surface that reflects light, improves damage detection, and reduces wrinkles and subgrade desiccation. It can also be easily tested for post-installation damage using equipment capable of performing spark testing in the field per ASTM D7240. This product is used in applications that require post-installation testing on the liner system to increase the quality of the project.



### AT THE CORE:

An HDPE geomembrane that contains an integrated, specially formulated conductive layer on the bottom surface.

### Product Specifications

These product specifications meet GRI GM13

Tested Property	Test Method	Frequency	Minimum Average Value			
			1.00 mm	1.50 mm	2.00 mm	2.50 mm
Thickness, (minimum average), mm Lowest individual reading	ASTM D 5994	every roll	1.00 0.90	1.50 1.35	2.00 1.80	2.50 2.25
Density, g/cm <sup>3</sup> . (min.)	ASTM D 1505	90,000 kg	0.940	0.940	0.940	0.940
Tensile Properties (each direction) Strength at Break, N/mm Strength at Yield, N/mm Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbbell, 50 mm/min  G.L. 50 mm G.L. 33 mm	9,000 kg	10 15 100 12	16 22 100 12	21 29 100 12	26 37 100 12
Tear Resistance, N	ASTM D 1004	20,000 kg	125	187	249	311
Puncture Resistance, N	ASTM D 4833	20,000 kg	267	400	534	667
Carbon Black Content <sup>(1)</sup> , % (Range)	ASTM D 1603*/4218	9,000 kg	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	20,000 kg	Note <sup>(2)</sup>	Note <sup>(2)</sup>	Note <sup>(2)</sup>	Note <sup>(2)</sup>
Asperity Height, mm	ASTM D 7466	second roll	0.45	0.45	0.45	0.45
Notch Constant Tensile Load <sup>(3)</sup> , hr	ASTM D 5397, Appendix	90,000 kg	300	300	300	300
Oxidative Induction Time, min	ASTM D 3895, 200°C; O <sub>2</sub> , 1 atm	90,000 kg	>100	>100	>100	>100
<b>TYPICAL ROLL DIMENSIONS</b>						
Roll Length <sup>(4)</sup> , m	Double-Sided Textured Single-Sided Textured		213 238	158 165	122 125	101 101
Roll Width <sup>(4)</sup> , m			6.86	6.86	6.86	6.86
Roll Area, m <sup>2</sup>	Double-Sided Textured Single-Sided Textured		1,461 1,633	1,084 1,132	837 858	693 693

NOTES:

- <sup>(1)</sup>GSE Leak Location White may have an overall ash content greater than 3.0% due to the conductive and white layers. These values apply to the non-conductive black layer only.
- <sup>(2)</sup>Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- <sup>(3)</sup>NCTL for GSE Leak Location White Textured is conducted on representative smooth geomembrane samples.
- <sup>(4)</sup>Roll lengths and widths have a tolerance of ±1%.
- GSE Leak Location White Textured is available in rolls weighing approximately 1,800 kg.
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77° C when tested according to ASTM D 746.
- \*Modified.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



**[ DURABILITY RUNS DEEP ]** For more information on this product and others, please visit us at [GSEworld.com](http://GSEworld.com), call 800.435.2008 or contact your local sales office.